

Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	1/6

EEMB CO., LTD

Polymer Li-ion Battery Specification

Model: LP325085-PCM-LD/

Capacity: 1200mAh

Prepared	Checked	Approved

Customer:

Customer Approval (Cus	stomer confirmation):	
Signature	Checked	Approved
Signature	CHECKEU	Approved

Address: Room ABCD,25/F, Block A, Fortune Plaza, NO.7060 Shennan Road Shenzhen, China

Postal code: 518040

Phone: 0086-755-83022275 FAX: 0086-755-83021966

http://www.eemb.com



Document Name	nt Name Document No.		Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	2/6

Catalog

Chapter	Content	Page
0	Catalog.	2
1	Scope.	3
2	Product Basic Characteristics.	3
2.1	Model	3
2.2	Capacity	3
2.3	Nominal Voltage	3
2.4	Weight	3
2.5	Internal Impedance	3
2.6	Dimension	3
2.7	Charge	3
2.8	Discharge	3
2.9	Operation Temperature	3
2.10	Storage Temperature	3
2.11	Storage Relative Humidity	3
3	Shape and Dimensions.	3
4	Appearance	3
5	Specification	4
5.1	Electrical Characteristics.	4
5.1.1	1C ₅ A rate discharge capacity	4
5.1.2	High temp. discharge capacity	4
5.1.3	Low temp. discharge capacity	4
5.1.4	Cycle Life	4
5.1.5	Capacity Retention	4
5.2	Acclimatization Characteristics.	4
5.2.1	High Temp. and High Humidity	4
5.2.2	Vibration	4
5.2.3	Drop	4
5.2.4	Low-pressure	4
5.3	Safety Characteristics.	5
5.3.1	Overcharge	5
5.3.2	Short-Circuit.	5
5.3.3	Heating	5
5.3.4	Temperature cycle	5
6	Spec of PCM	5-6
7	Battery Pack's dimension	7
8	Battery Pack's voltage and internal resistance.	7
9	Warranty	7
10	Matters needing attention.	7~8



Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	3/6

1. Scope


This product specification defines the requirements of the rechargeable polymer lithium-ion battery supplied to the customer by EEMB Co., Ltd.

2. Product Basic Characteristics

No.	Item		Characteristics		Remark
2.1	Model		LP325085		
2.2	Capacity	Nominal Capacity	1200	mAh	$0.2C_5A$
2.2	Сараспу	Minimum	1100	mAh	0.2C ₅ A
2.3	Nom	inal Voltage	3.7	V	
2.4		Weight	Approx. 24	g	
2.5	Intern	al Impedance	≤ 80	$m\Omega$	AC 1KHz(50% charge)
		Length	≤ 86	mm	
2.6	Dimension	Width	≤ 50.5	mm	
		Thickness	≤ 3.5	mm	
	Charge	Maximum Current	1200	mA	1.0C ₅ A (CC&CV)
2.7		Limited Voltage	4.200±0.020	V	
		End-of Current	24	mA	
2.8	Discharge	Maximum Current	2400	mA	2.0C ₅ A
2.0	Discharge	End Voltage	2.750±0.005	V	
2.9	Operation	Charge	0 ~ 45	$^{\circ}\!\mathbb{C}$	
2.9	Temperature	Discharge	- 20 ∼ +60	$^{\circ}\!\mathbb{C}$	
	C4	1 month	- 20 ∼ +60	$^{\circ}\mathbb{C}$	
2.10	Storage Temperature	3 month	- 20 ∼ +45	$^{\circ}\!\mathbb{C}$	
	Temperature	12 month	- 20 ∼ +25	$^{\circ}\!\mathbb{C}$	
2.11	Storage R	elative Humidity	65±20	%	

3. Shape and Dimensions (Unit: mm)

Item	Specification
Т	Max3.5
W	Max50.5
L	Max86
L1	Max87
L2	10±1
M	30±1
N	4±0.5





Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	4/6

4. Appearance

It shall be free from any defects such as remarkable scratches, breaks, cracks, discoloration, leakage, or middle deformation.

5. Specification

5.1 Electrical Characteristics

No.	Item	Criteria	Test Instructions
5.1.1	1C ₅ A rate discharge capacity	Discharge Capacity≥ Minimum Capacity	Full charge at 20 ± 5 °C, rest for 30 min, then discharge at the same temperature with $1.0C_5A$ to $2.75V$.
5.1.2	High temp. discharge capacity	Discharge Time≥54min	Full charge at 20 ± 5 °C, store at 55 ± 2 °C for 2h, then discharge at the same temperature with $1.0C_5A$ to $2.75V$.
5.1.3	Low temp. discharge capacity	Discharge Time≥4.25h	Full charge at $20\pm5^{\circ}$ C, store at -10° C $\pm2^{\circ}$ C for $16h\sim24h$, then discharge at the same temperature with $0.2C_5A$ to $2.75V$
5.1.4	Cycle Life	≥500 Cycles (0.5C ₅ A) ≥800 Cycles (0.2C ₅ A)	After full charge, rest for 10 min, then discharge at constant current to 2.75V, rest for 10 minutes. Repeat above steps until the two consecutive cycles of discharge time is less than the regulated time. (500 cycles≥96min,800 cycles≥240min)
5.1.5	Capacity Retention	Discharge Time≥4.5 h	After full charge, store at 20±5 °C for 28 days. Then discharge with 0.2C₅A to 2.75V

5.2 Acclimatization Characteristics

No.	Item	Criteria	Test Instructions
1521	High Temp. and High Humidity	no fire or explosion;	After full charge, store at $40^{\circ}\text{C} \pm 2^{\circ}\text{C} (90\% \sim 95\%\text{RH})$ for 48h. After test, place at $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ for 2h and then discharge with $1\text{C}_5\text{A}$ to end-voltage
5.2.2		leakage, no fire or	Batteries are vibrated 30 min in three mutually perpendicular
5.2.3	•	No leakage, no fire or explosion.	Batteries are dropped onto a hard board with the thickness of $18\sim20$ mm from at least 1meter height. Drop the batteries from six different directions and discharge them at $1C_5A$ to end-voltage.
5.2.4	Low-pressure		Put the batteries in a sealed vacuum and reduce internal pressure gradually to lower than 11.6 kpa. Keep for 6h



Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	5/6

5.3 Safety Characteristics

No.	Item	Criteria	Test Instructions			
	Overcharge		Put the batteries with thermocouple into the ventilation cabinet.			
5 2 1		No fire or evolution	Connect the polarities to constant voltage and adjust the current to 3			
5.3.1			C ₅ A, voltage to 4.8V. Charged the cells at 3C ₅ A current 20±5°C with a			
			voltage limit of 4.8V and Current approach 0 A.			
		No fire or	Put the batteries with thermocouple into the ventilation cabinet.			
522		explosion;	Batteries are short-circuited by connecting the positive and negative			
5.3.2		The maximum	terminals for 1h with a resistance load of $100m\Omega$. Watch the changes of			
		Temperature: 150°C	temperature. Test the temperature of the batteries until it drops to $10^\circ\mathrm{C}$.			
522	Heating	No fine on evaluation	Cell is heated in a circulating air oven at a rate of (5±2)°C per minute to			
5.3.3		No fire or explosion	130±2°C, and then placed for 30 minutes at 130±2°C			
			After full charge, place the battery in the temperature control box of			
			$20\pm5^{\circ}$ C, do the following steps:			
	-	No leakage, no fire	(1)Put the battery into test chamber of 75°C±2°C and keep for 6h.			
5.3.4			(2)Lower the temperature to -40±2°C and keep for 6h			
			(3)Temperature conversion time is no longer than 30 min			
			(4)Repeat the above three steps for 10 cycles.			
Note: 11	nless otherwis	se specified all tests	stated in this specification are conducted at the following conditions:			

Note: Unless otherwise specified, all tests stated in this specification are conducted at the following conditions: Temp.: 20 ± 5 °C; Relative Humidity: $25\%\sim85\%$.

6. Specification of PCM

The specification shall be applied to Lithium polymer battery protection circuit module manufactured by EEMB CO., LTD.

6.1.0 Basic Specification(T=25°C)


Item	Symbol	Symbol Content		Criterion	
	$V_{ m DET1}$	Over charge detection voltage		4.28±0.05V	
Over charge Protection	tV_{DET1}	Over charge detection delay time		0.96S-1.40S	
	V_{REL1}	Over charge release voltage		4.175±0.1V	
	V_{DET2}	Over discharge detection voltage		3.0±0.10V	
Over discharge protection	tV_{DET2}	Over discharge detection delay time		115ms-173ms	
	V_{REL2}	Over discharge release voltage		3.5±0.1V	
Limited to Max peak value current	Peak value		Constant time	2A	38
Limited to Max loading current	Constant			1A	
Chart protection		Detection condition		Exterior short circuit	
Short protection		Release condition		Cut short circuit	
Interior resistance	R_{DS}	Main loop electrify resistance		$R_{DS} \leq 70 \text{m}\Omega$	
Current consumption	I_{DD}	Current consume in normal operation		3.0μA Type 7.0μA Max	

*Note: These specs are guaranteed by design not by production tests




Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	6/6

6.2.0 PCM Circuit Diagram



7. Pack's Dimension



8. Pack's voltage and internal resistance

Voltage: 3.7~3.9V

Internal Resistance: $\leq 200 \text{m} \Omega$

9. Warranty

One year warranty after the date of production



Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	7/6

10. Matters needing attention

Strictly observes the following needing attention. EEMB will not be responsible for any accident occurred by handling outside of the precautions in this specification.

! Danger

- Strictly prohibits heat or throw cell into fire.
- Strictly prohibits throw and wet cell in liquid such as water, gasoline or drink etc.
- Strictly prohibits use leave cell close to fire or inside of a car where temperature may be above 60°C. Also do not charge / discharge in such conditions.
- Strictly prohibits put batteries in your pockets or a bag together with metal objects such as necklaces. Hairpins, coins, or screws. Do not store or transportation batteries with such objects.
- Strictly prohibits short circuit the (+) and (-) terminals with other metals.
- Do not place Cell in a device with the (+) and (-) in the wrong way around.
- Strictly prohibits pierce Cell with a sharp object such as a needle.
- Strictly prohibits disassemble or modify the cell.
- Strictly prohibits welding a cell directly.
- Do not use a Cell with serious scar or deformation.
- Thoroughly read the user's manual before use, inaccurate handling of lithium ion rechargeable cell may cause leakage, heat, smoke, an explosion, or fire, capacity decreasing.

! Warning

- Strictly prohibits put cell into a microware oven, dryer, or high-pressure container.
- Strictly prohibits use cell with dry cells and other primary batteries, or new and old battery or batteries of a different package, type, or brand.
- Stop charging the Cell if charging is not completed within the specified time.
- Stop using the Cell if abnormal heat, odor, discoloration, deformation or abnormal condition is detected during use, charge, or storage.
- Keep away from fire immediately when leakage or foul odor is detected.
- If liquid leaks onto your skin or clothes, wash well with fresh water immediately.
- If liquid leaking from the Cell gets into your eyes, do not rub your eyes. Wash them well with clean edible oil and go to see a doctor immediately.

! Caution

- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Charging with specific charger according to product specification. Charge with CC/CV method.
 Strictly prohibits revered charging. Connect cell reverse will not charge the cell. At the same time, it will reduce the charge-discharge characteristics and safety characteristics; this will lead to product heat and leakage.
- Store batteries out of reach of children so that they are not accidentally swallowed.
- If younger children use the Cell, their guardians should explain the proper handling.
- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Batteries have life cycles. If the time that the Cell powers equipment becomes much shorter than usual, the Cell life is at an end. Replace the Cell with a new same one.
- When not using Cell for an extended period, remove it from the equipment and store in a place with low humidity and low temperature.



Document Name	Document No.	Ver	Date	Page
LP325085-PCM-LD/ Specification	ZJQM-RD-SPC-A0352	0.0	2014-10-31	8/6

- While the Cell pack is charged, used and stored, keep it away from objects or materials with static electric charges.
- If the terminals of the Cell become dirty, wipe with a dry clothe before using the Cell.
- Storage the cell in storage temperature range as the specifications. After full discharged, we suggest that charging to 3.7~4.0V with no using for a long time.
- Do not exceed these ranges of the following temperature ranges:

Charge temperature range : 0° C to 45° C;

Discharge temperature range : -20° C to 60° C. Store less than 1 month : -20° C - $+60^{\circ}$ C Store less than 3 months : -20° C - $+45^{\circ}$ C Store less than 1 year : -20° C - $+25^{\circ}$ C

! Special Notice

Keep the cell in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.7~4.0V. And store the battery in cool and dry place.